



Bridging the gap between PA and PPA for E&E applications

Ultramid® One J

Ultramid® One J is a high-temperature polyamide (PA66/6T) outperforming PA66 in mechanical and dielectric properties in presence of humidity and at elevated temperatures. It allows easy processing similar to standard PA with low tool corrosion, thus closing the gap to the Ultramid® Advanced PPA portfolio. It has been proven that the mold temperature has no significant influence on the mechanical properties. Ultramid® One J shows high flowability and opens up new, colorful possibilities with even white color shades for miniaturization parts with electrical protection. The UL cards testify to excellent RTI and GWIT values, the used flame-retardant is without halogens.




chemical resistance
low water uptake
dimensional stability
hydrophobicity



ULTRAMID® ONE

Ultramid® One J 60X1

- V-0 UL rating at 0.4 mm
- High RTI values of up to 150 °C
- CTI of 600 V
- GWIT: 800 °C (0.8 mm)



Product	T _m [°C]	HDT A ISO 75 [°C]	E-modulus ISO 527 [GPa]	Tensile strength ISO 527 [MPa]
Ultramid® A3U42G6 (PA66 GF30 FR)	260	230	11.0/7.5	145/95
Ultramid® One J 60X1 V30 (66/6T GF30 FR)	280	257	11.0/9.1	145/110
Ultramid® Advanced T2340G6 (PA6T/66 GF30 FR)	310	>280	10.5/10.5	150/130

Easily colorable, next to orange and grey even for pure white products



Good dimensional stability

- Lower water uptake compared to PA66
- Small influence on properties due to low water uptake



High dimensional stability

Bridging the gap between PA66 and PPA

Ultramid® One J is bridging the gap between PA66 and PPA grades for key properties, also in conditioned state.


J

Mechanical properties

Ultramid® One J	Tensile modulus at 23 °C ISO 527-1/-2 [MPa]	Stress at break at 23 °C ISO 527-1/-2 [MPa]	Strain at break at 23 °C ISO 527-1/-2 [%]	Charpy unnotched impact strength at 23 °C ISO 179/1eU [kJ/m²]	Charpy notched impact strength at 23 °C ISO 179/1eA [kJ/m²]
60X1 V30	11,000 / cond. 9,100	145 / cond. 110	2.5 / cond. 3.3	65 / cond. 62	10 / cond. 10
206 V60 nat	- / -	- / -	2.4 / 2.6	90 / 90	15 / 15
219HT V35	- / -	200 / -	3 / -	- / -	- / -

Processing

Ultramid® One J	Melt temperature injection molding [°C]	Mold temperature injection molding [°C]
60X1 V30	285-300	90-110
206 V60 nat	280-300	90-110
219HT V35	270-310	85-110



Ultramid® One J

Product portfolio and applications

	Ultramid® One J	Reinforcement	Colors
Flame retardant	60X1 V30	30 % GF	bk, nat, grey, orange, white
Glass-fiber reinforced	206 V60	60 % GF	nat, white
	219HT V35	35 % GF	bk

Please check regional availability with your BASF contact.

Possible applications

For mainly E&E applications:

- Connectors
- MCBs, MCCBs
- Consumer electronics
- Electric shower

Ultramid® One J 219HT with high purity for fuel cell components.



The right material for the right part: choose the suitable material for your application!
PPA Product Selector on www.ppa.basf.com

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. (March 2022)

For further questions please contact the Ultra-Infopoint: +49 621 60-78780 / ultraplaste.infopoint@basf.com

www.ppa.basf.com